



DESCRIPTION

Paint in aerosol form, rich in zinc powder which offers high and long-lasting anticorrosive protection, creating a cold galvanizing film. It has great adhesion to almost all metallic surfaces. Ideal for protecting welded surfaces, pipes, tanks, and all metallic constructions which are exposed to corrosive factors.

PROPERTIES

- Viscosity: 18-25sec (Flow Cup DIN4, 20°C)
- Density: 1.1-1.2 g/L (Density Cup 100cm³/20°C, ASTM D – 1475)
- Pigment purity: Approx. 99.9%
- VOC content : 450 g/L
- Flash Point: -104°C
- Drying time
(1 Layer, Temperature 20°C, Humidity <65%):
 - Touch: 5-10min
 - Thorough dry: 1h
 - Maximum hardness: 24h
- Coverage: 4m²/L
- GLOSS (GLOSS METER 60°ASTM D – 1471):
0-10 GLOSS UNITS/MATT
- Film thickness: 40-45µm
- Can Pressure: 4bar (20°C), 8 bar (50°C)
- Contents: 400ml

INSTRUCTIONS FOR USE

APPLICATION

Remove all dust, rust, and oil from the surface. Protect the area which you don't want to be painted. Shake the can thoroughly and spray at a distance of 25-30cm from the surface. Try the spray on a testing surface. For better results apply 2-3 thin coats, 3-5 min apart. Due to the high density, the Zinc Spray must be shaken for at least 2 minutes after you hear the noise of the mixing balls. **Best application temperature: 10°C - 25°C.**

AFTER USE

Spray holding the inverted for 3". Clean the caps with solvent.

STORAGE

5-35°C. Do not store inside vehicles.

CAP SYSTEM



STANDARD CAP

- High Coverage
- Thin & Regular
- Gradual Spraying
- No drips

COLOR RANGE

ZINC MAXIMUM 500

SILVER



SAFETY

Request SDS

There are likely to be declinations in digital performance of shades. **ISSUED DATE: 2/9/2025**

VERSION: 02

*This information was composed to the best of our current knowledge. It provides no guarantees.
The data in this sheet is a result of extensive testing either by Cosmos Lac or its suppliers.
However always thoroughly check whether the product is fit to serve the purpose you mean it to work for.*